

### CHURCH

FEATURE	NORM	CHURCH
Process		DPL
Base Board	HDF (density 880–920kg/m <sup>3</sup> )	≥ 880kg/m <sup>3</sup>
Locking system	2–Lock system	Angle Lock
Edges		4 V painted
<b>Requirements for classification</b>		
Abrasion resistance	EN13329–Annex E	AC4
Impact resistance	EN13329	IC2
Stain resistance	EN438–2(group 1, 2 & 3)	Group 1 & 2: Grade 5 Group 3: ≥ Grade 4
Resistance to cigarette burns	EN438–2	Grade 4
Effect of furniture legs	EN424	No damage
Castor chair test (soft rolls)	EN425	No change in appearance
Thickness swelling	EN13329–Annex G	
<b>General requirements</b>		
Light fastness	EN 13329 Blue Wool Grey Wool	≥ Level 6 ≥ Level 5
Static indentation	En433	No visible change
Surface soundness	EN13329	≥ 1.60 N/mm <sup>2</sup>
Dimensions		8 x 191 x 1210mm
<b>Use and safety</b>		
Flame resistance	EN13501–1	Cfl–s1
Formaldehyde emission	EN717–1	E1
Slip resistance: Friction co–efficient	EN14041/EN13983	≥ 0.30 Class DS
<b>Logistics Information</b>		
Planks / Box		10 pieces
Sqm / Box		2.35m <sup>2</sup>
Weight / Sqmts		17.56kg
Guarantee		10 years as per manufacturers terms
Green Label		

